

OUR FINISHES: SUMMARY

Discover our new demonstration video on website www.mercadier-decoration.com

General Note : The strength of our finish products is tailored to common uses of a home, but their good performance in the time depends on strict adherence to data sheets during the implementation of products and maintenance that will be made thereafter

Training Centre in Aix-en-Provence
Information : info@centre-formation-decoration.com

1,349 € TTC / APPEL
+ 0,337 € TTC / MIN* 0 899 4 94 0 0 4

*depuis un poste fixe, hors éventuel service de votre région

DRAFT ->	Washbasin	Shower	Counter / Kitchen splahback	Decorative wall	Living room floors (lounge, dining room, bedroom)	Kitchen floors	Large passage floors (including public spaces)	Outdoor	Associated concrete	METHOD	ASPECTS
IMPREGNATOR				***					EBC PMB	IMPREGNATOR : 1 to 3 layers spaced from 1 to 4H	SEMI MAT to SATIN ACCORDING TO THE NUMBER OF LAYERS
IMPREGNATOR + MONO AQUA VARNISH				**	***	** 3 layers			EBC PMB RBX SC+	IMPREGNATOR : 2 to 3 layers spaced from 1 to 4h MONO VARNISH : 2 to 3 layers spaced from 2h	SEMI-MAT / SATIN
IMPREGNATOR + SOLVENT PROTECTOR		***		**	**			***	EBC PMB	IMPREGNATOR : 2 to 3 layers spaced from 1 to 4h PROTECTOR : 2 layers spaced from de 2h to 8h according to temperature	SATIN
									RBX SC+	IMPREGNATOR : 2 to 3 layers spaced from 1 to 4h PROTECTOR 2 to 3 layers spaced from 2h to 8h according to temperature	
IMPREGNATOR + BICOMPONENT SOLVENT VARNISH TO DILUTE	***		***					**	EBC PMB	IMPREGNATOR : 2 to 3 layers spaced from 1 to 4h BICOMPONENT SOLVENT VARNISH TO DILUTE 2 layers spaced from 12h	SEMI-MAT / SATIN
IMPREGNATOR + VARNISH BIAQUA SOILS LARGE PASSAGE	***	*** without standing water	***	***	***	***	***	** (outdoor sheltered outdoors without standing water)	EBC PMB RBX SC+	IMPREGNATOR : 2 to 3 layers spaced from 1 to 4h VARNISH BIAQUA SOILS : 2 to 3 layers in the same day spaced from 2h mini	SEMI MAT
Legends							CAUTION : Before moving the protections, concrete will have a residual humidity lower than 1% a surface temperature up to 10/12°C				
***	Ideal (a few rare precautions cf Datasheet)										
**	Adapted : (precautions cf Datasheet)										
	Not Adapted										